上海海冰新材料科技有限公司
Shanghai H&B New Materials Co.,Ltd
联系方式/Contacts：+86 21-31225039/ www.lithlon.com

技术数据表/Technical Data Sheet

产品: Product:	HB-F211B		
规格 Specification	高强度、高吹胀比吹膜料 High strength and high blowing ratio		
应用 Application	吹膜，适合单层及多层共挤等 Film Blowing, suitable for single and multi-layer co-extrusion, etc.		
参考加工条件 Reference Processing Conditions	加工温度150℃-190℃，吹胀比1.8-6 Processing temperature: 150℃-190℃, Blow ratio: 1.8-6		
测试项目 Items	单位 Unit	参数值 Parameter Value	测试方法 Method
熔融指数 Melt Flow	g/10min	11.00~16.00	ASTM D1238
密度 Density	g/cm^3	1.10~1.20	ASTM D792
百颗粒重 Medium Weight	g/100 chips	1.90~2.10	H&B
含水率 Moisture Content	ppm	≤ 1200	H&B
外观 Appearance		正常/REGULAR	(目测/Visual)
杂质 Contamination		无/NONE	(目测/Visual)
包装 Package	kg/包	25	H&B

备注/Note:

本报告根据我们的经验得出。如用于特殊用途，使用者应根据实际生产情况判定产品的适用性，我们不做额外担保
This report is based on our experience. For special purposes, the user shall determine the applicability of the product according to the actual production conditions, and we will not provide additional guarantee